



THE SIAM REFRACTORY INDUSTRY CO.,LTD.

1 Siam Cement Road , Bangsue , Bangkok 10800 , THAILAND

Tel : (66 2) 5863242-52 , Fax : (66 2) 5872149 , 5862982

05 / 10

Data Sheet

C SiC 150

Classification : High-Alumina Low Cement Castable, Silicon Carbide Containing

Physical Properties :

Maximum Service Temperature	°C	1600
Maximum Grain Size of Aggregates	mm	12.5
Approx. Weight Required for Casting	kg/m ³	2750
Approx. Amount of Water Required for Casting	%	5.0-6.0
Bulk Density After Drying at 110 °C	kg/m ³	2780
Modulus of Rupture After Drying at 110 °C	kg/cm ²	120
Modulus of Rupture After Heating at 1100 °C	kg/cm ²	95
Cold Crushing Strength After Drying at 110 °C	kg/cm ²	650
Cold Crushing Strength After Heating at 1100 °C	kg/cm ²	950
Permanent Linear Change After Heating at 1600 °C	%	-0.20

Chemical Composition :

Alumina (Al ₂ O ₃)	%	64.0
Silica (SiO ₂)	%	16.0
Iron Oxide (Fe ₂ O ₃)	%	1.0
Lime (CaO)	%	1.4
Silicon Carbide (SiC)	%	15.0

Thermal Conductivity :

at 400 °C	W/m.K	3.25
at 500 °C	W/m.K	3.00
at 600 °C	W/m.K	2.85
at 800 °C	W/m.K	2.75
at 1000 °C	W/m.K	2.75

The above data are typical values of which the properties of the samples tested according to the internal procedure and standard of Siam Refractory generally accepted by our customers for many years. The above data can not be used for specification or guarantee purpose. Siam Refractory reserves the right to update the above data and change our internal procedure and standard without any prior notice.

Approved by :  Date : May 19, 2010
Quality Assurance Manager