

หจก. โคว์หลี่เซ้ง

ตัวแทนจำหน่ายอย่างเป็นทางการของ

หจก. สยามอุตสาหกรรมวัสดุทนไฟ

CAST 15 LW

CLASSIFICATION	Insulating Castable ASTM C 401 Class S		
PHYSICAL PROPERTIES	Max. Service Temperature	°C	1500
	Approx. Weight Required for Casting	kg/m ³	1450
	Approx. Amount of Water Required for Casting	%	22
	Bulk Density After Drying at 110 °C	kg/m ³	1500
	Modulus of Rupture After Drying at 110 °C	kg/cm ²	30
	Modulus of Rupture After Heating at 1480 °C	kg/cm ²	40
	Cold Crushing Strength After Drying at 110 °C	kg/cm ²	150
	Cold Crushing Strength After Heating at 1480 °C	kg/cm ²	250
	Permanent Linear Change After Heating at 1480 °C	%	-0.80
CHEMICAL COMPOSITION	Alumina (Al ₂ O ₃)	%	66.0
	Silica (SiO ₂)	%	15.0
	Iron Oxide (Fe ₂ O ₃)	%	1.5
	Lime (CaO)	%	15.0
THERMAL CONDUCTIVITY	400 °C	(W/m.K)	0.59
	600 °C	(W/m.K)	0.60
	800 °C	(W/m.K)	0.61
	1000 °C	(W/m.K)	0.63

The above data are typical values of which the properties of the samples tested according to the internal procedure and standard of Siam Refractory generally accepted by our customers for many years. The above data can not be used for specification or guarantee purpose. Siam Refractory reserves the right to update the above data and change our internal procedure and standard without any prior notice.