

EAZYFLOW 80

CLASSIFICATION	High-Alumina Low Cement Castable (Self Flow)		
PHYSICAL PROPERTIES	Max. Service Temperature	°C	1700
	Max. Grain Size of Aggregates	mm	12.5
	Approx. Weight Required for Casting	kg/m ³	2800
	Approx. Amount of Water Required for Casting	%	6.0-6.5
	Bulk Density After Drying at 110 °C	kg/m ³	2850
	Modulus of Rupture After Drying at 110 °C	kg/cm ²	80
	Cold Crushing Strength After Drying at 110 °C	kg/cm ²	500
	Permanent Linear Change After Heating at 1400 °C	%	+0.05
CHEMICAL COMPOSITION	Alumina (Al ₂ O ₃)	%	80.0
	Silica (SiO ₂)	%	12.0
	Iron Oxide (Fe ₂ O ₃)	%	1.0
	Lime (CaO)	%	1.5
THERMAL EXPANSION	400 °C	%	0.33
	800 °C	%	0.52
	1000 °C	%	0.70
	1200 °C	%	0.88
	1400 °C	%	1.05
THERMAL CONDUCTIVITY	400 °C	(W/m.K)	2.25
	500 °C	(W/m.K)	2.20
	600 °C	(W/m.K)	2.14
	800 °C	(W/m.K)	2.08
	1000 °C	(W/m.K)	2.05
	1200 °C	(W/m.K)	2.05

The above data are typical values of which the properties of the samples tested according to the internal procedure and standard of Siam Refractory generally accepted by our customers for many years. The above data can not be used for specification or guarantee purpose. Siam Refractory reserves the right to update the above data and change our internal procedure and standard without any prior notice.

